

MP220

Injection Molding

Description

- High Adhesion Metal Plating ABS

Applications

- Automobile Radiator Grill, Molding

Properties	Method	Unit	MP220
Physical			
Specific Gravity , 23°C	ASTM D792		1.04
Mold Shrinkage , 23°C, 3.2mm , 23°C	ASTM D955	%	0.4 ~ 0.7
Melt Flow Rate , 220°C, 10kg	ASTM D1238	g/10min	20
Mechanical			
Tensile Strength at Yield , 23°C, 50mm/min, 3.2mm	ASTM D638	Mpa	42
Tensile Elongation at Yield , 23°C, 50mm/min, 3.2mm	ASTM D638	%, (Min)	5
Tensile Elongation at Break , 23°C, 50mm/min, 3.2mm	ASTM D638	%, (Min)	25
Tensile Modulus , 23°C, 50mm/min, 3.2mm	ASTM D638	MPa	2350
Flexural Strength , 23°C, 15mm/min, 3.2mm	ASTM D790	Mpa	73
Flexural Modulus , 23°C, 15mm/min, 3.2mm	ASTM D790	MPa	2550
Izod Impact Strength , Notched, 3.2mm, 23°C	ASTM D256	J/m	290
Izod Impact Strength , Notched, 3.2mm, -30°C	ASTM D256	J/m	120
Izod Impact Strength , Notched, 6.4mm, 23°C	ASTM D256	J/m	230
Izod Impact Strength , Notched, 6.4mm, -30°C	ASTM D256	J/m	100
Rockwell Hardness , R-Scale	ASTM D785		110
Thermal			
HDT , Edgewise, 1.82MPa, 6.4mm, Unannealed	ASTM D648	°C	91
VICAT , 50N, 50°C/h	ASTM D1525	°C	101

Note

Typical values can be used only for the purpose of selecting material, and there can be variation within normal tolerances for various colors. Values given should not be interpreted as specification and not be used for designing part or tool. All properties, except melt flow rate are measured by injection molded specimens after 48 hours storage at 23°C, 50% relative humidity.

Updated Date : 16-Nov-17 Issued Date : 6-Mar-18

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.

MP220

Injection Molding

Description

- High Adhesion Metal Plating ABS

Applications

- Automobile Radiator Grill, Molding

Processing Guide (Injection Molding)

Processing Parameters	Unit	Value
Drying Temperature	°C	70 ~ 80
Drying Time	hrs	3 ~ 4
Minimum Moisture Content	%	0.01
Melt Temperature	°C	230 ~ 250
Cylinder Temperature , Rear	°C	200 ~ 220
Cylinder Temperature, Middle	°C	210 ~ 230
Cylinder Temperature , Front	°C	220 ~ 240
Nozzle Temperature	°C	220 ~ 240
Mold Temperature	°C	50 ~ 70
Back Pressure, Hydraulic Type	kg/cm ²	10 ~ 20
Screw Speed	rpm	80

Note

Back Pressure & Measuring Speed are only mentioned as general guidelines. These may not apply or need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding.

Updated Date : 16-Nov-17 Issued Date : 6-Mar-18

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.