

SCHEDA TECNICA**ABS NERO RIGRANULATO**

Item	Test method	Test condition	Unit	Value	
PHYSICAL					
Melt Index	ASTM D 1238	200°C/5kg	g/10min	15	±5%
MECHANICAL					
Tensile Strength	ASTM D 638	50mm/min	kg/cm ²	200	±5%
Tensil Modulus	ASTM D 638	50mm/min	kg/cm ²	4,5	±5%
Izod Impact	ASTM D 256	1/4",23°C	kg cm/cm	15	±5%
THERMAL					
Heat Deflection	ASTM D 648	1/4"18,56kg/cm ²	°C	85	±5%
CHARACTERISTIC					
				MD impact	

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Terplast cannot anticipate all conditions under which this information and our products of other manufactures in combination with our products may be used. Terplast accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Terplast sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.