

Polyacetal (POM)

**DURACON®**

M270-57

WK2001

Food Contact  
Safety, Multi-national  
Certification Of  
Drinkingwater Safety

# General Properties of M270-57

table1-1 General Properties (ISO)

Item	Unit	Test Method	Food Contact Safety,Multi-national Certification Of Drinkingwater Safety
			M270-57
			High Flow,Fast Molding Cycle
Color			WK2001
ISO(JIS)quality-of-the-material display:		ISO11469 (JIS K6999)	>POM<
Density	g/cm <sup>3</sup>	ISO 1183	1.41
Water absorption (23℃,24hrs,1mmt)	%	ISO 62	-
MFR (190℃、 2.16kg)	g/10min	ISO 1133	27
MVR (190℃, 2.16kg)	cm <sup>3</sup> /10min	ISO 1133	23
Tensile strength	MPa	ISO 527-1,2	66
Strain at break	%	ISO 527-1,2	20* <sup>1</sup>
Tensile modulus	MPa	ISO 527-1,2	2,900
Flexural strength	MPa	ISO 178	91
Flexural modulus	MPa	ISO 178	2,600
Charpy notched impact strength (23℃)	kJ/m <sup>2</sup>	ISO 179/1eA	7.0
Temperature of deflection under load (1.8MPa)	℃	ISO 75-1,2	95
Coefficient of linear thermal expansion (23 - 55℃、 Flow direction)	x10 <sup>-5</sup> /℃	Our standard	11
Coefficient of linear thermal expansion (23 - 55℃、 Transverse direction)	x10 <sup>-5</sup> /℃	Our standard	11
Electric strength (3mmt)	kV/mm	IEC 60243-1	19
Volume resistivity	Ω·cm	IEC 60093	1 × 10 <sup>14</sup>
Surface resistivity	Ω	IEC 60093	1 × 10 <sup>16</sup>
Volume resistivity (Our standard)	Ω·cm		-
Surface resistivity (Our standard)	Ω		-
Mold Shrinkage (60×60×2mmt, Flow direction)	%	ISO 294-4	1.8
Mold Shrinkage (60×60×2mmt, Transverse direction)	%	ISO 294-4	1.8
Rockwell hardness	M(Scale)	ISO2039-2	88
Specific wear amount (Thrust, vs C-Steel, material side, pressure 0.49MPa, 30cm/s)	x10 <sup>-3</sup> mm <sup>3</sup> /(N·km)	JIS K7218	-
Specific wear amount (Thrust, vs C-Steel, steel side, pressure 0.49MPa, 30cm/s)	x10 <sup>-3</sup> mm <sup>3</sup> /(N·km)	JIS K7218	-
Coefficient of Dynamic Friction (Thrust, vs C-Steel, pressure 0.49MPa, 30cm/s)		JIS K7218	-

Item	Unit	Test Method	Food Contact Safety, Multi-national Certification Of Drinkingwater Safety
			M270-57
			High Flow, Fast Molding Cycle
Specific wear amount (Thrust, vs C-Steel, material side, pressure 0.98MPa, 30cm/s)	$\times 10^{-3} \text{mm}^3/(\text{N} \cdot \text{km})$	JIS K7218	1.0
Specific wear amount (Thrust, vs C-Steel, steel side, pressure 0.98MPa, 30cm/s)	$\times 10^{-3} \text{mm}^3/(\text{N} \cdot \text{km})$	JIS K7218	0.01>
Coefficient of Dynamic Friction (Thrust, vs C-Steel, pressure 0.98MPa, 30cm/s)		JIS K7218	0.4
Specific wear amount (Thrust, vs M90-44, material side, pressure 0.06MPa, 15cm/s)	$\times 10^{-3} \text{mm}^3/(\text{N} \cdot \text{km})$	JIS K7218	30
Specific wear amount (Thrust, vs M90-44, M90-44 side, pressure 0.06MPa, 15cm/s)	$\times 10^{-3} \text{mm}^3/(\text{N} \cdot \text{km})$	JIS K7218	60
Coefficient of Dynamic Friction (Thrust, vs M90-44, pressure 0.06MPa, 15cm/s)		JIS K7218	-
Flammability		UL94	HB
The yellow card File No.			E45034
Appropriate List number of Ministerial Ordinance for Export Trade Control			Item 16 of Appendix -1

\*1) Nominal strain at break

All figures in the table are the typical values of the material and not the minimum values of the material specifications.

## **NOTES TO USERS**

- All property values shown in this brochure are the typical values obtained under conditions prescribed by applicable standards and test methods.
- This brochure has been prepared based on our own experiences and laboratory test data, and therefore all data shown here are not always applicable to parts used under different conditions. We do not guarantee that these data are directly applicable to the application conditions of users and we ask each user to make his own decision on the application.
- It is the users' responsibility to investigate patent rights, service life and potentiality of applications introduced in this brochure. Materials we supply are not intended for the implant applications in the medical and dental fields, and therefore are not recommended for such uses.
- For all works done properly, it is advised to refer to appropriate technical catalogs for specific material processing.
- For safe handling of materials we supply, it is advised to refer to the Safety Data Sheet "**SDS**" of the proper material.
- This brochure is edited based on reference literature, information and data available to us at the time of creation. The contents of this brochure are subject to change without notice upon achievement of new data.
- Please contact our office for any questions about products we supply, descriptive literatures or any description in this brochure.

DURACON® is a registered trademark of Polyplastics Co., Ltd. in Japan and other countries.

## **POLYPLASTICS CO., LTD.**

JR Shinagawa East Bldg.,  
18-1, Konan 2-chome, Minato-ku, Tokyo, 108-8280 Japan  
Tel: +81-3-6711-8610 Fax: +81-3-6711-8618

<http://www.polyplastics.com/en/>