

LG ABS AF365F

LG Chem Ltd. - Acrylonitrile Butadiene Styrene

Monday, October 7, 2024

General Information

Product Description

Flame Retardant, Heat resistant

Application

Electric parts, IT/OA device

TV, monitor housing

General

Material Status	• Commercial: Active	
Availability	• Asia Pacific • Europe	• Latin America • North America
Features	• Flame Retardant	• Good Heat Resistance
Uses	• Electrical Parts	• Television Housings
RoHS Compliance	• RoHS Compliant	
Processing Method	• Injection Molding	

ASTM & ISO Properties¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.18	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	75	g/10 min	ASTM D1238
Molding Shrinkage - Flow (23°C, 3.20 mm, Injection Molded)	0.40 to 0.70	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ²			ASTM D638
Yield, 23°C, 3.20 mm, Injection Molded	41.2	MPa	
Tensile Elongation ²			ASTM D638
Yield, 23°C, 3.20 mm, Injection Molded	5.0	%	
Tensile Elongation ²			ASTM D638
Break, 23°C, 3.20 mm, Injection Molded	> 20	%	
Flexural Modulus ³ (23°C, 6.40 mm, Injection Molded)	2260	MPa	ASTM D790
Flexural Strength ³ (23°C, 6.40 mm, Injection Molded)	66.7	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-30°C, 3.20 mm, Injection Molded	59	J/m	
-30°C, 6.40 mm, Injection Molded	49	J/m	
23°C, 3.20 mm, Injection Molded	210	J/m	
23°C, 6.40 mm, Injection Molded	160	J/m	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 23°C, Injection Molded)	105		ASTM D785

customer is responsible for determining whether products and the information in this document are appropriate for customer's use and for ensuring that customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. seller assumes no obligation or liability for the information in this document. **no warranties are given; all implied warranties of merchantability or fitness for a particular purpose are expressly excluded.**

LG ABS AF365F

LG Chem Ltd. - Acrylonitrile Butadiene Styrene

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 0.45 MPa, Unannealed, 6.40 mm, Injection Molded	91.0	°C	ASTM D648
Deflection Temperature Under Load 1.8 MPa, Unannealed, 6.40 mm, Injection Molded	84.0	°C	ASTM D648
Vicat Softening Temperature	90.0	°C	ASTM D1525 ⁴
RTI Elec (1.8 to 3.0 mm)	75.0	°C	UL 746B
RTI Imp (1.8 to 3.0 mm)	75.0	°C	UL 746B
RTI Str (1.8 to 3.0 mm)	75.0	°C	UL 746B
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.7 mm		V-1	
2.0 mm		V-0	
		5VB	
3.0 mm		V-0	
		5VA	

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	80 to 90	°C
Drying Time	3.0 to 4.0	hr
Rear Temperature	170 to 190	°C
Middle Temperature	180 to 200	°C
Front Temperature	190 to 210	°C
Nozzle Temperature	200 to 230	°C
Processing (Melt) Temp	200 to 230	°C
Mold Temperature	40 to 60	°C
Back Pressure	0.490 to 0.981	MPa
Screw Speed	30 to 60	rpm

Injection Notes

Minimum Moisture Content: 0.01%

Notes

¹ Typical properties: these are not to be construed as specifications.

² 50 mm/min

³ 15 mm/min

⁴ Rate A (50°C/h), Loading 2 (50 N)