

TECHNICAL DATA SHEET

Product : HiPrene H710

Test Items	Method(ASTM)	Unit	Result
Melt Index	D1238	g/10min	0.7
Density	D792	g/cm ³	0.90
Tensile Strength	D638	MPa	36
Elongation at Break	D638	%	150
Izod Impact @23°C	D256	J/m	58
Izod Impact @-10°C	D256	J/m	19
Flexural Strength	D790	MPa	45
Flexural Modulus	D790	MPa	1,500
Heat Distortion Temp.	D648	°C	90
Rockwell Hardness	D785	R	115

Notes : Typical properties; not to be constructed as specification.
 Values may vary according to different environment conditions and/or devices.